



# T1000™ Stampable Overlay

## Technical Data Sheet T1000 03

**FOR PROFESSIONAL USE ONLY.** Read all applicable and current product information for your project: Technical Data Sheet (TDS), Color Chart, Installation Guide, Material Safety Data Sheet (MSDS). All information is available for download online at [www.butterfieldcolor.com](http://www.butterfieldcolor.com) and at point of purchase.

MasterFormat™ Guide Specifications, and Butterfield Color® Architectural Details and Specifications are available for the specifier/designer. All information is available for download online at [www.butterfieldcolor.com](http://www.butterfieldcolor.com) and at point of purchase.

**1. Description:** T1000™ Stampable Overlay is a polymer modified cementitious topping formulated for resurfacing structurally sound, non-moving concrete floors and exterior hardscapes. The overlay provides a durable surface suitable for stamping with Butterfield Color® Stamping Tools or textured with Butterfield Color® Texture Rollers. The cured product creates an abrasion resistant surface suitable for pedestrian and automobile traffic. It is an ideal system for restoring worn or color-blemished concrete, out of level surfaces or correcting construction errors. Properly applied to clean and sound concrete, T1000™ Stampable Overlay is freeze/thaw resistant. 21-day compressive strength is 5250 psi (36.2 MPa).

T1000™ Stampable Overlay is a precise blend of graded sand, cement, and polymer, which allow for thin applications. It is a pre-packaged material that is mixed on the job site with clean water and can be stamped textured or roller textured. Application thickness ranges from 1/8 inch (3 mm) to a maximum of 1/2 inch (13 mm).

T1000™ Stampable Overlay is packaged in medium gray or white colors. Those base colors may be colored with a Uni-Mix® Color Pack. 24 colors are available. Refer to the Uni-Mix® Integral Colorant color chart for available colors. Colors are formulated for use with T1000™ Stampable Overlay medium gray unless noted otherwise. Custom colors and colors selected from the Perma-Cast® Shake-on Color Hardener color chart can be formulated with ample lead-time. **Note:** When T1000™ Stampable Overlay is mixed with a Uni-Mix® Color Pack, the cured color will not be an exact match to concrete colored with integral color or color hardener. T1000™ Stampable Overlay medium gray, white or colored materials may be stained by applying Elements™ Transparent Stain or Perma-Cast® Sierra Stain™. Read the Elements™ Transparent Stain or Perma-Cast® Sierra Stain™ Technical Data Sheet before installing product. All information is available for download online at [www.butterfieldcolor.com](http://www.butterfieldcolor.com) and at point of purchase. **Perma-Cast® Sierra Stain™** **Note:** A dilution rate of 3 parts water to 1 part Perma-Cast® Sierra Stain™ is recommended when using with T1000™ Stampable Overlay.

**2. Limitations:** T1000™ Stampable Overlay is formulated for use over thoroughly clean, structurally sound, and non-moving concrete. Surface preparation is required. New concrete must be fully cured before applying the product. Maximum applied thickness is 1/2" (13 mm) in a single application. Do not install product if ambient and substrate temperatures are not between 45°F (7°C) and 85°F (30°C), unless site conditions can be modified to correct for temperature extremes.

T1000™ Stampable Overlay should not be installed in areas subject to steel wheel traffic, strong chemicals, periodic water immersion, or hydrostatic pressure. The cured overlay surface should be sealed for ease of cleaning, particularly on interior floors. Extend existing substrate control joints up through the overlay to minimize random cracks in the overlay. Random cracks in the existing substrate may transfer through the cured overlay even if they are repaired prior to application.

**3. Packaging:** T1000™ Stampable Overlay is available in 55 lb. (25 kg) bags. Uni-Mix® Color Pack weights vary from 0.5 lb.-1.25 lb. (0.23 kg-0.57 kg), depending on the color selected. Colors are formulated for use with T1000™ Stampable Overlay medium gray unless noted otherwise.

**3.1 SHELF LIFE:** 2 years in original, unopened containers, in dry storage.

**4. Coverage:** The coverage rates of one 55 lb. (25 kg) unit of T1000™ Stampable Overlay are approximately:

- 24 sq. ft. at 1/4" thick (2.2 m<sup>2</sup> at 6 mm thick)
- 16 sq. ft. at 3/8" thick (1.5 m<sup>2</sup> at 9 mm thick)
- 12 sq. ft. at 1/2" thick (1.1 m<sup>2</sup> at 13 mm thick)

Coverage will vary depending on the depth of installation, substrate texture, and method of application and finishing. When imprinting T1000™ Stampable Overlay with Butterfield Color® Stamping Tools, the overlay should be applied at a thickness equal to the depth of the mortar joint that will be imprinted with the stamping tool. Material applications that are too thin or too thick may not allow for the accurate transfer of pattern and texture into the overlay product.

**5. Substrate Preparation:** Remove all potential bond breakers such as grease, oil, paints, sealants, drywall taping compound, mastics and other contaminants on the surface. New concrete must be fully cured and free from curing and sealing compounds, laitance, or dusting. Slick, hard-troweled floors must be opened and roughened. Random cracks must be repaired, but may still transfer through the cured overlay.

Surface preparation may include high-pressure washing, grinding, scarifying, shot blasting, or sandblasting, depending on the type of residue being removed and surface profile required. Refer to the International Concrete Repair Institute Guideline #03732 for information on achieving a Concrete Surface Profile (CSP) of 3-5. Failure to remove all contamination that impedes the adhesion of T1000™ Stampable Overlay will cause the topping to delaminate. Detergents or soaps should not be used since they may leave a surface residue. Do not acid etch as it may weaken the surface. Unsound concrete must be removed down to sound concrete.

**6. Priming:** Shake or mix well before use. Mix 1:1 with water. Apply an even coat of Butterfield Color® T1000™ Primer to the prepared substrate using a paint roller or bristled brush. Do not apply primer over damp concrete. Coverage is approximately 200 sq. ft. per gallon (4.9 m<sup>2</sup>/L). Take care to protect adjacent surfaces from overspray or splash. Once the application of T1000™ Primer has dried tack free, installation may proceed. **Note:** If the initial application of primer contains bubbles or pinholes, a second application of primer is required before installing T1000™ Stampable Overlay. Additionally, rough or very porous concrete substrates may also require a second application of primer. Read the Butterfield Color® T1000™ Primer Technical Data Sheet before applying. All information is available for download online at [www.butterfieldcolor.com](http://www.butterfieldcolor.com) and at point of purchase.

T1000™ Stampable Overlay may be applied as much as 24 hours after application of the primer. Do not expose the primed surface to moisture or contamination. After 24 hours or if the primed surface





# T1000™ Stampable Overlay

## Technical Data Sheet T1000 03

3 CONCRETE FINISHES  
 BUTTERFIELD COLOR  
 Engineered Concrete Performance

is exposed to moisture or becomes dirty, the primer must be reapplied. **Note:** On stamping or texturing jobs, when installation is to be made in multiple pours over a common concrete substrate area, care must be taken to protect the prepared and primed concrete from contamination. Read the Butterfield Color® T1000™ Primer Technical Data Sheet before installing product. All information is available for download online at [www.butterfieldcolor.com](http://www.butterfieldcolor.com) and at point of purchase.

**7. Mixing:** Prior to mixing, store all materials in a shaded or cool environment. Chilling the water is advisable during hot weather. Mix and install when ambient temperatures are between 45°F-85°F (7°C-30°C). Use 3.7-4.0 quarts potable water per 55 lb. (3.5-3.8 L/25 kg) bag of Butterfield Color® T1000™ Stampable Overlay. When temperature or humidity affect water demand, make small adjustments to the amount of mixing water as needed to achieve proper working consistency. Do not over water. Measure the water accurately and consistently from batch to batch. Always add water to the container first. Then, if color is to be used, add the Uni-Mix® Color Pack while mixing, using a 600 rpm drill and a paddle or mortar mixer, followed by the Butterfield Color® T1000™ Stampable Overlay. Continue to mix for a minimum of 3 minutes until a smooth, uniform, lump-free consistency and a streak-free color has been achieved. If mixture loses its plasticity, do not retemper with water or add previously mixed material to new batches.

**8. Installation:** Mark the location of all working joints in the concrete substrate, in order to saw cut joints through the overlay exactly over those existing joints. The overlay joints must be full depth and as wide as the existing substrate joints.

All repair and patching compounds must be fully cured before applying T1000™ Stampable Overlay and T1000™ Primer. Maximum applied thickness is 1/2 inch (13 mm) in a single application. **Note:** When repair and patching compounds are used, creating a test area using the patch compounds with T1000™ Stampable Overlay is recommended to ensure a similar absorption rate is achieved, otherwise ghosting may occur. For thicker applications, allow material to dry for 8 hours after placement at 70°F (21°C), and then apply a second layer. Place additional layers in the same manner. Do not apply T1000™ Stampable Overlay over standing or visible moisture on the primed surface.

Always maintain a wet edge during application. Terminate pours at existing joint lines, walls or other fixed objects. If a pour is terminated in the center of the floor or at a doorway between rooms for example, delineate the stopping point with a bulkhead form.

**8.1. TROWEL APPLICATION:** Once material is thoroughly mixed, immediately pour T1000™ Stampable Overlay from the mixing pail onto the concrete surface. A pool trowel or fresno may be used to distribute the product. Similarly, a gauge rake can be used to distribute the overlay to a specific and consistent depth before lightly finishing with a pool trowel. This is particularly important when the T1000™ Stampable Overlay will be stamped with Butterfield Color® Stamping Tools or textured with Butterfield Color® Texture Rollers. Keep tools free of build up by cleaning frequently with water before the T1000™ Stampable Overlay dries completely. Apply material at a consistent thickness to minimize random shrinkage cracking.

Do not overwork the surface with the pool trowel. Do not hard trowel T1000™ Stampable Overlay. Finishing time will vary with temperature, wind, humidity, use of a primer or an evaporation retarder. Do not mix or apply more material than can be handled effectively for the installation. If the surface finish of the overlay is not satisfactory, scrape and remove the problem area before it starts to dry and then reapply the overlay. **Note:** The reapplied material may be visually different from the surrounding surface.

**8.2. STAMPING OR TEXTURING:** Place or distribute freshly mixed T1000™ Stampable Overlay material by pool trowel or gauge rake over properly prepared concrete substrate. A gauge rake is strongly recommended in order to achieve a consistent depth to receive the pattern and texture. Imprinting time will vary widely depending on temperature, humidity and overlay thickness. Begin stamping as soon as mixture has set sufficiently to achieve a clean impression, usually 20 to 60 minutes after placement. Apply Butterfield Color® Clear Liquid Release to the area prior to placing stamps or using texture rollers. Existing control joints should be mapped out prior to placement of the T1000™ Stampable Overlay and re-cut before cracking occurs. Protect T1000™ Stampable Overlay from rain for 24 hours after placement. Read the Butterfield Color® Clear Liquid Release Technical Data Sheet before installing product. All information is available

for download online at [www.butterfieldcolor.com](http://www.butterfieldcolor.com) and at point of purchase.

**9. Curing:** T1000™ Stampable Overlay is self-curing. However, during hot weather or windy conditions polyethylene sheets may be used to minimize plastic shrinkage cracking. The method of curing may affect the final color of T1000™ Stampable Overlay. Verify curing method and timing with a mock-up. Once the curing method has been determined, utilize consistently throughout the installation. Curing time varies with ambient and substrate temperatures, and humidity. The surface can be walked on gently approximately 4 hours after placement at 70°F (21°C). Cure for a minimum of 96 hours before opening the surface to automobile traffic. A full 28-day cure is required before heavy traffic or exposure to freeze/thaw cycling.

Control joints are required. Saw cutting of control joints directly over the existing control joints in the concrete substrate should be completed within 14 hours after installation, once the surface has gained adequate strength so as not be damaged by the saw cutting process. Cool ambient and surface temperatures may delay sawing.

**10. Antiquing:** Perma-Tique™ Antiquing Agent may be used to add a secondary coloring effect to the T1000™ Stampable Overlay. Once the T1000™ Stampable Overlay has cured for a minimum of 24 hours and can withstand foot traffic without marring the surface, the surface should be cleaned to remove any contaminants and residue from the stamping process. **Note: A test area should be cleaned to ensure no damage is caused by the cleaning process before proceeding to clean the entire area.** Once finished with cleaning the surface, the application of Perma-Tique™ Antiquing Agent may begin. Read the Technical Data Sheet on Perma-Tique™ Antiquing Agent prior to installation. All information is available for download online at [www.butterfieldcolor.com](http://www.butterfieldcolor.com) and at point of purchase. Once dry, the Perma-Tique™ Antiquing Agent should be sealed to lock it in.

**11. Staining:** For natural appearing color variations, T1000™ Stampable Overlay can be colored with Elements™ Transparent Concrete Stain or Perma-Cast® Sierra Stain™. The stain may be applied to a stamped or textured surface. The T1000™ Stampable Overlay should be fully cured, clean, and dry before applying stain. Do not apply Elements™ Transparent Concrete Stain or Perma-Cast® Sierra Stain™

3 CONCRETE FINISHES  
 BUTTERFIELD COLOR  
 Engineered Concrete Performance



# T1000™ Stampable Overlay

## Technical Data Sheet T1000 03

3 CONCRETE FINISHES  
 Engineered Concrete Performance  
**BUTTERFIELD**  
**COLOR**

on top of the Perma-Tique™ Antiquing Agent. Do not utilize aggressive cleaning methods until the T1000™ Stampable Overlay is thoroughly cured. Read the Elements™ Transparent Concrete Stain or Perma-Cast® Sierra Stain™ Technical Data Sheet before installing product. All information is available for download online at [www.butterfieldcolor.com](http://www.butterfieldcolor.com) and at point of purchase. **Perma-Cast® Sierra Stain™ Note:** A dilution rate of 3 parts water to 1 part Perma-Cast® Sierra Stain™ is recommended when using with T1000™ Stampable Overlay.

**12. Sealing:** Clear Guard® Cure and Seal should be applied after the surface has cured for a minimum of 72 hours at 70°F (21°C). Application of a sealer prior to 72 hours may weaken the surface of an overlay. Sealed surfaces may become slippery when wet. Sealed surfaces will require maintenance. Read the Clear Guard® Cure and Seal Technical Data Sheet before installing product. All information is available for download online at [www.butterfieldcolor.com](http://www.butterfieldcolor.com) and at point of purchase.

**13. Repair:** Damage to the overlay surface should be repaired with T1000™ Stampable Overlay. Once the cause of the damage has been determined and corrected, the deteriorated area should be cut and chipped to the minimum applied depth of the product, 1/8 inch (3 mm). If damage to the underlying concrete exceeds the maximum allowable thickness of T1000™ Stampable Overlay, 1/2 inch (13 mm), use a suitable patching compound to repair the concrete, prior to the application of T1000™ Stampable Overlay or apply T1000™ Stampable Overlay in multiple applications, not exceeding 1/2 inch (13 mm) in a single application.

The repair cavity should be chipped to a uniform depth to minimize random shrinkage cracking in the repair materials. The perimeter of the repair cavity should be saw cut or chipped out to prevent feather edging of the patching compound. All dust and contamination should be removed before application of the patching compound or T1000™ Stampable Overlay. The repaired area may appear differently than adjacent surfaces. Repair materials and methods should be evaluated and confirmed with a repair mock-up.

**14. Quality Control:** Cast a job site sample at least 21 days prior to the installation for approval of color and finish. Utilize all materials, tools, and techniques from the actual job in the mock-up. Consistent batching, pouring, finishing, curing, sealing, and preparation techniques, will ensure the uniformity of architectural concrete. Verify adequate wet and dry slip resistance. Discuss maintenance requirements. Site visits by Butterfield Color, Inc. Personnel are for making technical recommendations only and not for supervising or providing quality control. Maintenance requirements should also be discussed.

**WARNING: HARMFUL IF INHALED. THIS PRODUCT CONTAINS SILICA (CRYSTALLINE QUARTZ) AND PORTLAND CEMENT. DO NOT BREATHE DUST. PROLONGED EXPOSURE CAN RESULT IN SILICOSIS. USE WITH ADEQUATE VENTILATION. PORTLAND CEMENT IS IRRITATING TO EYES AND SKIN AND MAY CAUSE ALKALI BURNS. ALWAYS USE PROTECTIVE GLASSES, GLOVES AND DUST MASK (NIOSH/MSHA TC-21C APPROVED). IMMEDIATELY AFTER USE WASH ANY AREA OF EXPOSED SKIN. IF CONTACT**

IS MADE WITH EYES FLUSH THOROUGHLY WITH WATER, DO NOT RUB. IF INHALED, MOVE TO FRESH AIR. IF SYMPTOMS DEVELOP OR PERSIST, OR IF INGESTED, SEEK MEDICAL ATTENTION. **DO NOT TAKE INTERNALLY. KEEP OUT OF REACH OF CHILDREN AND ANIMALS.** DISPOSE OF ALL RESIDUAL MATERIALS ACCORDING TO LOCAL, STATE, AND FEDERAL REGULATIONS. READ THE MATERIAL SAFETY DATA SHEET BEFORE USING OR HANDLING THIS PRODUCT. ALL INFORMATION IS AVAILABLE FOR DOWNLOAD ONLINE AT [WWW.BUTTERFIELDCOLOR.COM](http://WWW.BUTTERFIELDCOLOR.COM) AND AT POINT OF PURCHASE.

**LIMITED WARRANTY AND DISCLAIMER – EXCLUSIVE REMEDY:** Butterfield Color, Inc. (“BC”) warrants that this product conforms to its published specifications when it is shipped. THIS LIMITED WARRANTY IS THE EXCLUSIVE WARRANTY AND THERE ARE NO OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. BC does not warrant any particular method of use or application of the product or its performance under any particular condition. If this product does not conform to its published specifications when shipped, we will replace the product as your exclusive remedy. Any action for breach of the limited warranty or any other liability arising from this product must be brought within 90 days of receiving the product. BC is not liable for consequential damages or personal injury arising from the use, storage or handling of this product.

**Suggested Short Form Specification for Butterfield Color® T1000™ Stampable Overlay:**

Prepare overlay surfaces and prime with Butterfield Color® T1000™ Primer according to manufacturer’s instructions. Mix Butterfield Color® T1000™ Stampable Overlay with Uni-Mix® Color Pack [ ] according to manufacturer’s instructions. Trowel-apply Butterfield Color® T1000™ Stampable Overlay at a thickness of [ ] inches, minimum. Clean tools frequently to avoid build up of overlay materials. Apply Butterfield Color® Clear Liquid Release according to manufacturer’s instructions and imprint using Butterfield Color® Stamping Tools using [ ] pattern. [Optional: Mix Butterfield Color® Perma-Cast® Antiquing Release powder with Butterfield Color® Clear Liquid Release in a pump sprayer according to manufacturer’s instructions. Keep mixture well agitated during application to prevent settling. Apply liberally and consistently over stamped area. Allow antiquing mixture to thoroughly dry before sealing.] Seal concrete with 2 coats Butterfield Color® Clear Guard® Cure and Seal with slip-resistive additive according to manufacturer’s instructions.

3 CONCRETE FINISHES  
 Engineered Concrete Performance  
**BUTTERFIELD**  
**COLOR**